

Pure Performance LINER

Production Unit: Gruvön Mill, KM7

Product Description

Pure Performance is produced from 100% virgin fibres. The characteristics for this grade are high and consistent quality combined with superior runnability.

Approvals

Pure Performance is produced in compliance with FDA and BfR packaging norms.

Grammages

125, 135, 160, 175, 200 g/m²

Certifications

Gruvön Mill is certified in accordance with ISO 9001, ISO 14001 and FSSC 22000.

Property	Unit							Method
Grammage	g/m ²		125	135	160	175	200	ISO 536
Thickness	µm		150	165	195	215	245	ISO 534
Air resistance	s		80	80	80	80	80	ISO 5636-5
SCT	CD	kN/m	2,8	3,1	3,6	4,0	4,5	ISO 9895
Tensile stiffness	MD	kN/m	1200	1400	1550	1700	1800	ISO 1924
	CD	kN/m	450	500	650	700	750	
Burst strength	kPa		590	640	770	850	970	ISO 2758
Scott Bond	J/m ²		350	350	350	350	350	TAPPI T569
Roughness	PS	ml/min	250	290	350	370	400	ISO8791-2
Brightness	%		75	75	75	75	75	ISO 2470
Cobb	PS	g/m ²	26	26	26	26	26	ISO 535
	RS	g/m ²	40	40	40	40	40	
Moisture	%		8,0	8,0	8,0	8,0	8,0	ISO 287

MD = Machine Direction

CD = Cross Direction

Test climate: 50% RH, 23°C

Rev. 202004

The table shows typical data for a range of grammages.