

SteriWrap 2004

IMPREGNATED MG KRAFT PAPER

Production Unit : Beetham

End uses

SteriWrap 2004 is designed for steam sterilisation for hospital applications.

SteriWrap 2004 possesses good softness, drapeability & wet strength characteristics.

Grammage

60 g/m²

Available in white (441) or green (443)

Materials

SteriWrap 2004 is produced from pure, white Kraft pulp and consists entirely of primary virgin fibre.

Approvals

SteriWrap 2004 is produced in compliance with ISO 11607-1, EN868-2

SteriWrap 2004 is a BSI Kitemarked paper.

Certification

Beetham mill is certified in accordance with ISO 9001, ISO 14001 and BS OHSAS 18001

Property	Unit				Method
Grammage	g/m ²		58		On Line QCS
Tensile strength	N/15mm kN/m *	MD CD	40 17	2.6* 1.1*	ISO 1924-3
Wet Tensile strength	N/15mm kN/m *	MD CD	6 5	0.4* 0.3	ISO 3781
Tear strength	mN		MD 560		ISO 1974
Burst strength	kPa		150		ISO 2758
Wet Burst strength	kPa		60		ISO 3689
Porosity Bendtsen	ml/min		310		ISO 5636-3
Water Absorbance	g/m ²		MG 18		ISO 535
pH Aqueous hot extract	pH		6.5		ISO 6588
Water Repellency	s		MG 60		EN 868
Drape	cm		MD 13.5		EN 868

MD = Machine Direction

CD = Cross Direction

MG = MG side

FS = Felt Side

Test climate: 50% RH, 23C

Issue: 2 Rev: 4 2006-11

The table shows typical values.

* indicates derived value, for information only.